

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
8 November 2001 (08.11.2001)

PCT

(10) International Publication Number
WO 01/83845 A2

(51) International Patent Classification: **C23C 16/26**

(21) International Application Number: **PCT/JP01/03595**

(22) International Filing Date: **26 April 2001 (26.04.2001)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(30) Priority Data:
09/563,807 **2 May 2000 (02.05.2000)** **US**

(71) Applicants: **ITAC LIMITED [JP/JP]**; 24-5, Kitaotsuka
2-chome, Toshima-ku, Tokyo 170-0004 (JP). **NAGATA
SEIKI KABUSHIKI KAISHA [JP/JP]**; 24-5, Kitaotsuka
2-chome, Toshima-ku, Tokyo 170-0004 (JP).

(72) Inventors: **BAKOUNINE, Oleg Markovich**; S. Rasin
St., 58-29, Ekaterinburg, 620063 (RU). **PLOTNIKOV,**

Serguei Aleksandrovich; Krasnolesia St., 14/3-15,
Ekaterinburg, 620046 (RU). **TRAKHTENBERG, Iliia
Shmulevich**; Sheinkman St., 45-53, Ekaterinburg, 620014
(RU). **UEMURA, Kensuke**; 4-21-9, Shichirigahama-hi-
gashi, Kamakura-shi, Kanagawa 248-0025 (JP).


(74) Agents: **KAJI, Yoshiyuki et al.**; Recruit Shin Osaka
Building, 14-22, Nishinakajima 5-chome, Yodogawa-ku,
Osaka-shi, Osaka 532-0011 (JP).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM,
HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK,
LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX,
MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL,
TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European


[Continued on next page]

(54) Title: **DIAMOND-LIKE CARBON THIN FILM COATING PROCESS, PRODUCT PRODUCED THEREBY, AND INCORPORATION THEREOF ON MAGNETIC RECORDING MEDIA SENSORS**



View A-A

A Floppy Disc Head



B Magnetic Tape

(57) Abstract: Wear-resistant and low-friction hard amorphous, diamond-like carbon coating (DLC) is formed directly on an external surface of a magnetic recording media sensor (MRMS). The coating demonstrates a high degree of hardness, low friction coefficient and moderate electric resistivity, providing abrasion-proof, low-clogging, static electricity-deterrent properties.

WO 01/83845 A2



patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations
- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

Published:

- without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

DESCRIPTION

DIAMOND-LIKE CARBON THIN FILM COATING PROCESS, PRODUCT PRODUCED THEREBY, AND INCORPORATION THEREOF ON MAGNETIC RECORDING MEDIA SENSORS

TECHNICAL FIELD

The present invention relates to a wear-resistant coating which exhibits properties of low-friction, low-clogging and resistance against static electricity. The invention relates further to a process for forming the coating and products utilizing same.

BACKGROUND ART

The aforementioned type coatings are generally formed over surfaces which are prone to wear, scratching, collecting of debris and formation of static electricity due to exposure to an external rubbing action. Magnetic recording media sensors (MRMS) which may be used for reading and/or writing of magnetically stored information are typical examples of such surfaces.

Coatings which have been recently developed are suitable for use in hard disc and floppy-disc reading/writing heads, video and audio heads, magnetic discs

and magnetic tapes, magnetic counters, etc. As an MRMS operates in close and/or direct contact with other MRMS surfaces, debris and abrasive particles move relative thereto.

In accordance with conventional practice, the MRMS and its surface are coated by a protective film which includes at least two layers having different hardness and electrical conductivity. Moreover, such film is coated by means of chemical vapor deposition (CVD) with heating assistance. Due to such heating assistance, deformation of substrate and creation of inner stress is unavoidable, and the performance of the particular MRMS is consequently decreased. The external surface of the coating has a higher degree of hardness for providing an abrasion-proof surface, and the inner layer has comparatively low resistivity in order to abate the influence of static electricity. However, the use of multilayered film increases the coating thickness and/or decreases its wear resistance, and increases the production cost.

Accordingly, it is an object of the invention to provide an effective abrasion-proof, low-friction, low-clogging, static electricity erasing, thin film coating method.

It is a further object of the invention to provide an apparatus for forming such thin film coating which inhibits damage of the MRMS even when operating in close or direct contact with other MRMS surfaces, and in the presence of debris and abrasive particles moving relative thereto, even at low temperatures.

DISCLOSURE OF INVENTION

In accordance with these and other objects of the invention, an MRMS is coated directly with hard amorphous carbon (also referred to herein by the term "diamond-like carbon" or DLC) films having a high degree of hardness, smooth surface and low friction coefficient, to provide an abrasion-proof surface, which significantly abates the influence of static electricity and which collects a minimum amount of debris. These properties can be realized using vacuum pulse arc carbon sputtering and ion beam surface treatments. For purposes herein, the term "MRMS" will refer not only to the magnetic recording media sensor itself, but also alternatively to the media used with such sensor.

According to a preferred embodiment of the present invention, the content of sp^3 -bonded carbon (hereinafter sometimes referred to as " sp^3 ") in the coating is within the range of about 30 to about 85 percent. The Vickers hardness is in the range of about 3000 to about 9000 kg/mm². The deposition process advantageously employs ion beams, and the coating process may be done with repetition of deposition and etching using such ion beams. Further, the beams may be scanned. One or more substrate holders are advantageously provided in a location in the deposition chamber out of projections of the ion and carbon sources

in the direction of gravity, an electrical resistance of the substrate holder or holders to earth junction being set in a range of about $1\text{ M}\Omega$ to about $10\text{ M}\Omega$.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1A is a schematic representation of an MRMS in the form of a floppy disc head employing a coating formed by the process in accordance with the invention;

Fig. 1B is a schematic representation MRMS in the form of a magnetic tape employing a coating formed by the process in accordance with the invention;

Fig. 2 is a schematic diagram showing an apparatus for deposition of the hard amorphous (diamond-like) carbon in accordance with the present invention;

Fig. 3A is a schematic diagram showing crack propagation in the coating depending on sp^3 proportion;

Fig. 3B is a schematic diagram showing another form of crack propagation in the coating depending on sp^3 proportion;

Figs. 4A and 4B are schematic diagrams showing anti-body damage and the MRMS clogging respectively due to the coating failure;

Fig. 5 is a schematic diagram of an MRMS holder, and sources and gravity direction relative a position thereof in the deposition chamber;

Fig. 6 is a schematic diagram of an ion beam controlling field intensity vs. ion treatment time;

Fig. 7 is a schematic diagram of the MRMS holder; and

Fig. 8 is a schematic diagram of the coating thickness vs. deposition-etching process time.

BEST MODE FOR CARRYING OUT THE INVENTION

Referring now to the figures, and in particular, Figs 1A and 1B, examples of different MRMS are illustrated, which incorporate the thin film coating in accordance with the invention. As shown in Fig. 1A, the MRMS (floppy disc) is comprised of a substrate 1, a magnetic media layer 2, and a protective layer 3. The external surface of MRMS (floppy disc head) 100 is coated with an amorphous, diamond-like carbon film 11 having a high degree of hardness, low friction coefficient and moderate electric resistivity providing abrasion-proof low-clogging, anti-static electricity properties thereby providing resistance against the tendency to wear, scratching, collecting of debris and static electricity due to an externally applied rubbing action. Similarly, Fig. 1B shows a tape head 12 and a tape comprising a tape layer 13, a magnetic media layer 14 and an amorphous, diamond-like carbon film 11'.

Turning now to Fig. 2, a typical apparatus for deposition of a hard amorphous (diamond-like) carbon by pulse arc vacuum sputtering of graphite on a surface, in accordance with the present invention is depicted schematically. The surface to be coated may be made, for example, of semiconductor, glass, metal ceramics, organic resins, magnetic substance, etc.

The apparatus comprises a vacuum chamber 4, carbon pulse arc source (or sources) 5, gas ion source (or sources) 6, metal arc source (or sources) 7, a gas feeding system 8, substrate (MRMS) holder (or holders) 9 and a pumping system 10 including a pressure control, an oil diffusion pump and mechanical pump (not shown). Gas ion source 6, carbon pulse arc source 5 and metal arc source 7 are supplied with magnetic deviating coils (not shown) for controlling gas ion, carbon ion and metal ion beams, respectively.

During operation of the above-described apparatus, electric pulse arc sputtering of a graphite target with pulse frequency regulated from about 1 to about 30 Hz is performed, and carbon plasma is produced by carbon pulse arc source 5 and condensed on substrate 9, forming a hard amorphous (diamond-like) carbon coating thereon.

Gas ion source 6 may be employed for preliminary cleaning and/or etching of the surface of the substrate (MRMS) and/or for intermediate and/or final etching of the coating.

Gas ion energy of, for example, about 1 KeV to about 6 KeV is advantageously employed. Suitable gases include, for example, hydrogen, neon, argon, xenon, krypton, oxygen, nitrogen, hydrocarbons, fluorocarbons and mixtures thereof. The substrate temperature is maintained in a range of about +20° to about +300°C by means of a temperature control unit (not shown). The diamond-like properties of the coatings deposited thereby, namely hardness, wear resistance, low friction coefficient and chemical inertness, are observed in this temperature range and, if necessary, in a range of about +100° to about +400°C. Ion beams are employed to clean and etch the substrate surface and deposit coatings conventionally. Disadvantages are: i) nonhomogeneity of the beam restricts the treated surface size; ii) in many cases power of the beam is limited by possible overheating of the substrates. However beam(s) scanning permits enlargement of the treated/deposited surface and cleaning/etching/deposition time less than the pumping time about 30 times, so as to result in a substantial increase of treated substrates area at the same quality. Arc metal source(s) 7 may be used to deposit an adhesive sublayer and/or to modify the coating properties, such as hardness and electric conductivity.

EXAMPLE 1

Hard amorphous (diamond-like) carbon is deposited onto MRMS, the latter provided in the form of floppy disc heads, as shown in Fig. 3A. The sp^3 proportion is 75%, the Vickers hardness is 8000 kg/mm², the resistivity is 1×10^5 Ω cm and the coating thickness is 10 nanometers. Due to optimal coating structure, the coating is shown to be stable and wear resistant.

The resultant MRMS demonstrates no noise, and output signal range in the 90-100% level for the designed receiving signal for over 400 hours.

COMPARATIVE EXAMPLE 2

Hard amorphous (diamond-like) carbon is deposited onto MRMS, in the form of floppy disc heads. The sp^3 proportion 19 is lower than 30%, the hardness is lower than 3000 kg/mm² and the sensor life is the same as for the non-coated sensor. Within 50 hours, noise is detected and receiving output signal decreases to lower than 85% of the designed receiving signal.

COMPARATIVE EXAMPLE 3

Hard amorphous (diamond-like) carbon (also referred to by the term "DLC") is deposited onto MRMS, in the form of floppy disc heads. The sp^3 proportion 19 is higher than 85% and the hardness is higher than 9000 kg/mm². As a result, internal stresses inside the DLC 11 rise and self-peeling of the coating

sections is experienced. Even in cases where self-peeling does not occur, cracks 20 induced by external action easily reach the DLC-substrate surface and propagate therealong, as shown in Fig. 3B, such that the DLC 11 peels off the substrate.

COMPARATIVE EXAMPLE 4

With a hardness higher than 9000 kg/mm², cracks induced by wearing easily reach the DLC-substrate surface and propagate therealong, such that the DLC peels off the substrate. The area of DLC 11" remaining on the surface results in damage 21 to magnetic media and/or collection of debris 22, as shown Fig. 4A and 4B. This results in inappropriate sensor operation within 50 hours operation. It is to be understood that sp³ porportion and hardness correlate, and the quality of the output of MRMS as a result of damage or collection of debris becomes impaired, namely, more noise and a weaker signal result, due to a longer distance to the magnetic media.

EXAMPLE 5

One or more substrate holders (not shown) each suitable for accommodating one or more substrates 9 are located out of the projection (region within dotted lines) in the gravity direction (as indicated by the downwardly pointing arrow) of the source(s) and parts associated therewith, as shown in Fig. 5.

The beam is designated 26, the electrode 27 and the source 5. The MRMS yield is 99.99%.

COMPARATIVE EXAMPLE 6

One or more substrate holders each suitable for accommodating one or more substrates are positioned at least partially inside of projection in the gravity direction of sources and associated parts. The MRMS yield drops from 99.99% (Example 5) to 90% due to falling dust particles deposited onto the substrates.

EXAMPLE 7

The ion source maximum power is 1 kVA, with a treated surface diameter of 100 mm. About 500 MRMS, in the form of floppy disc heads are locatable in this area. If the ion source power is 1 KVA, all the sensors would be overheated and adversely affected during treatment ($>80^{\circ}\text{C}$), so the power is 0.5 kVA, and treatment duration, 1 minute.

EXAMPLE 8

The same ion source (Example 7), with linearly scanned beam, and the treated surface has dimensions of 100 to 250 mm, scanning frequency of 0.1 to 1 Hz and controlling field intensity which is sine-like. About 1500 sensors may be

located at this area. If the ion source power is 1 KVA, none of the sensors are overheated during treatment ($<50^{\circ}\text{C}$), so the treatment duration is 1.5 minute.

EXAMPLE 9

The same ion source (Example 8) with linearly scanned beam is used. The roughness of the treated surface is reduced through ion beam radiation. Table 1 shows the DLC surface roughness R in micrometers and R (DLC) of the same unit without etching. The rated thickness is 3 microns in Table 1 and 2 microns in Table 2. Both in Tables 1 and 2, DLC surface roughness is lower than initial substrate roughness.

TABLE 1

R	R (DLC)
0.2	0.4
0.25	0.5
0.50	1.0
0.65	1.25
0.75	1.55
1.2	2.0
1.7	3.2

TABLE 2

R	R (DLC)
0.15	0.35
0.25	0.30
0.40	0.70
0.70	0.65
0.70	0.55
0.85	0.75

EXAMPLE AND COMPARATIVE EXAMPLE 10

The same ion source with linearly scanned beam is used. The treated surface has dimensions of 100 to 250 mm at a scanning frequency of 1 Hz and in which a controlling field intensity is saw-like, as shown in FIG. 6. At the middle part of the treated surface, the etched depth is the same as at margins thereof. However, when the controlling field intensity is sine like, at the middle part of the treated surface the etched depth is 10% more than at the margins.

EXAMPLE AND COMPARATIVE EXAMPLE 11

The pulse arc carbon source maximum frequency is 30 Hz and a uniformly deposited surface has a diameter of 100 mm. About 500 sensors may be located at this area. If the carbon source frequency is 2 Hz, all of the sensors will be

overheated (adversely affected) during treatment ($>80^{\circ}\text{C}$), so the frequency must be 1 Hz, and treatment duration, 1 minute.

EXAMPLE 12

The same carbon source with linearly scanned beam is used. A uniformly treated surface has dimensions of 100 to 250 mm. About 1500 sensors may be located at this area. If the carbon source frequency is 2 Hz, none of the sensors are overheated during treatment ($<50^{\circ}\text{C}$), so the treatment duration is 1 minute. Scanning is step-like (two fixed positions, synchronically with source pulses).

EXAMPLE 13

The beam is scanned randomly and/or has some rotation when applied for treatment of an MRMS having a complicated shape, or when the MRMS or their holder dimensions are larger than the beam size. This achieves a homogeneous coating layer.

EXAMPLES AND COMPARATIVE EXAMPLES 14

The MRMS is a video head. Sensors holder(s) assembly insulation to vacuum chamber (=earth) during ion etching and DLC deposition may be regulated in range $0\ \Omega$ to $10\ \text{M}\Omega$. The percentage number of heads spoiled due

to electric discharge near the gap during DLC deposition vs. holder-to-earth insulation is shown in Table 3.

TABLE 3

Holder-to-earth insulation	Percent of the sensors spoiled
0.5	1.1
0.7	0.5
0.8	0.3
1.0	0.1
4.0	0.03
6.0	0.04
8.0	0.02
10.0	0.1
20.0	0.5

The substrate (sensor) holder 9 is made of a suitable plastic, in these examples, nylon. To fix the substrates (sensors) 11 and release static electricity, metal wires 17 held in frames 18 are adopted as shown in Fig. 7.

COMPARATIVE EXAMPLE 15

A DLC coating 10 nm thick is deposited directly (without intermediate and final etching) onto an MRMS, namely a floppy disc head. Surface roughness is 3

nm and friction coefficient is 0.2. Working life of the sensor coated is within 50 hours and receiving output signal decreased lower than 85% of designed receiving signal.

EXAMPLE 16

A DLC coating 13 nm thick is deposited without intermediate etching and final etched with oxygen ions to 10 nm. Surface roughness is 1.8 nm and friction coefficient is 0.08. Working life of the sensor coated is at least 400 hours and receiving output signal is within 90-100% of designed receiving signal.

EXAMPLE 17

A DLC coating 12 nm thick is deposited with intermediate etching with oxygen ions in the following way: five steps consisting of 3 nm DLC deposition and 1 nm etching each as shown in Fig 8. Surface roughness is 0.8 nm and friction coefficient is 0.04. Working life of the sensor coated is over 400 hours and receiving output signal is over 95% of designed receiving signal.

Having described preferred embodiments of the invention with reference to the accompanying drawings, it is to be understood that the invention is not limited to those precise embodiments, and that various changes and modifications may be effected therein by one skilled in the art without departing from the scope or spirit of the invention as defined in the appended claims.

INDUSTRIAL APPLICABILITY

This present invention is suitable as an effective abrasion-proof, low-friction, low-clogging, static electricity erasing, thin film coating method.

This invention is further suitable as an apparatus for forming such thin film coating which inhibits damage of the MRMS even when operating in close or direct contact with other MRMS surfaces, and in the presence of debris and abrasive particles moving relative thereto, even at low temperatures.

CLAIMS

1. A magnetic media sensor, comprising:
 - a substrate having a sensing surface;
 - a hard amorphous carbon coating (DLC) directly coating said sensing surface, said DLC having an sp^3 bonded carbon content within a range of about 30% to about 85%, and a hardness in a range of 3000 kg/mm² to 9000 kg/mm².
2. An apparatus for forming a hard amorphous coating on a magnetic media sensor, comprising:
 - at least one carbon source;
 - at least one ion source, and additional metal source(s), and the sputtering vector from the sources to substrate(s) holder(s) is out of projection of sources and their parts projections to the gravity direction.
3. A method of producing a hard amorphous carbon coating on surface of a magnetic media sensor
 - employing ion beams and these beams are electrically sawlike scanned.

4. A method according to claim 3, wherein the deposition process employs beams, and said beams being electrically randomly scanned.




FIG.1 (A) Floppy Disc Head




FIG.1 (B) Magnetic Tape




FIG.2




FIG.3 (A)




FIG.3 (B)




FIG. 4 (A)




FIG. 4 (B)




FIG.5




FIG.6




FIG.7




FIG.8

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
8 November 2001 (08.11.2001)


PCT

(10) International Publication Number
WO 01/083845 A3

- (51) International Patent Classification⁷: **C23C 16/26**, G11B 5/00, C23C 14/32, 14/06
- (21) International Application Number: **PCT/JP01/03595**
- (22) International Filing Date: **26 April 2001 (26.04.2001)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
09/563,807 2 May 2000 (02.05.2000) **US**
- (71) Applicants: **ITAC LIMITED** [JP/JP]; 24-5, Kitaotsuka 2-chome, Toshima-ku, Tokyo 170-0004 (JP). **NAGATA SEIKI KABUSHIKI KAISHA** [JP/JP]; 24-5, Kitaotsuka 2-chome, Toshima-ku, Tokyo 170-0004 (JP).
- (72) Inventors: **BAKOUNINE, Oleg Markovich**; S. Rasin St., 58-29, Ekaterinburg, 620063 (RU). **PLOTNIKOV, Serguei Aleksandrovich**; Krasnolesia St., 14/3-15, Ekaterinburg, 620046 (RU). **TRAKHTENBERG, Ilia Shmulevich**; Sheinkman St., 45-53, Ekaterinburg, 620014 (RU). **UEMURA, Kensuke**; 4-21-9, Shichirigahama-higashi, Kamakura-shi, Kanagawa 248-0025 (JP).
- (74) Agents: **KAJI, Yoshiyuki** et al.; Recruit Shin Osaka Building, 14-22, Nishinakajima 5-chome, Yodogawa-ku, Osaka-shi, Osaka 532-0011 (JP).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.


[Continued on next page]

(54) Title: **MAGNETIC SENSOR HAVING DIAMOND-LIKE CARBON THIN FILM**



View A-A

A Floppy Disc Head



B Magnetic Tape

(57) Abstract: Wear-resistant and low-friction hard amorphous, diamond-like carbon coating (DLC) is formed directly on an external surface of a magnetic recording media sensor (MRMS). The coating demonstrates a high degree of hardness, low friction coefficient and moderate electric resistivity, providing abrasion-proof, low-clogging, static electricity-deterrent properties.

WO 01/083845 A3



(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

— *as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations*

Published:

— *with international search report*

Declarations under Rule 4.17:

- *as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations*
- *as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations*
- *as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations*

(88) Date of publication of the international search report:
29 August 2002

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

INTERNATIONAL SEARCH REPORT

onal Application No

PCT/JP 01/03595

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C23C16/26 G11B5/00 C23C14/32 C23C14/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C23C G11B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 858 477 A (WEILER MANFRED ET AL) 12 January 1999 (1999-01-12) column 4, line 26-46 column 8, line 23-31 ---	1
X	US 5 930 077 A (BABA KAZUHIRO ET AL) 27 July 1999 (1999-07-27) abstract ---	1
X	WO 95 18442 A (SCHULTZ ALLAN E ;SEAGATE TECHNOLOGY (US)) 6 July 1995 (1995-07-06) page 3, line 19 -page 4, line 16 ---	1
X	US 4 992 153 A (BERGMANN ERICH ET AL) 12 February 1991 (1991-02-12) column 5, line 26-36 figure 1 --- -/--	2



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

20 November 2001

Date of mailing of the international search report

28/11/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Castagné, C

INTERNATIONAL SEARCH REPORT

ional Application No

PCT/JP 01/03595

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	REPENNING D: "MEC:CH-COATINGS PRODUCED BY ARC-IONPLATING PROCESS" LE VIDE: SCIENCE, TECHNIQUE ET APPLICATIONS, SFV, FR, vol. 51, no. 276, 1 April 1995 (1995-04-01), pages 197-209, XP000534677 ISSN: 1266-0167 page 2 ----	2
X	US 5 192 523 A (WU RICHARD L ET AL) 9 March 1993 (1993-03-09)	3
Y	claim 6 ----	4
Y	US 4 751 100 A (OGAWA KAZUFUMI) 14 June 1988 (1988-06-14) column 3, line 23-38 -----	4

INTERNATIONAL SEARCH REPORT

Information on patent family members

Original Application No

PCT/JP 01/03595

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5858477	A	12-01-1999	AU 3224297 A	05-01-1998
			AU 3293097 A	05-01-1998
			EP 0906636 A1	07-04-1999
			EP 0909445 A1	21-04-1999
			JP 2000512053 T	12-09-2000
			WO 9745834 A1	04-12-1997
			WO 9745855 A1	04-12-1997
US 5930077	A	27-07-1999	JP 2531438 B2	04-09-1996
			JP 7006340 A	10-01-1995
WO 9518442	A	06-07-1995	SG 46309 A1	20-02-1998
			WO 9518442 A1	06-07-1995
			EP 0737354 A1	16-10-1996
			JP 9507329 T	22-07-1997
			US 5644455 A	01-07-1997
US 4992153	A	12-02-1991	EP 0394661 A1	31-10-1990
			JP 2285072 A	22-11-1990
US 5192523	A	09-03-1993	NONE	
US 4751100	A	14-06-1988	JP 1584048 C	22-10-1990
			JP 2008371 B	23-02-1990
			JP 60001625 A	07-01-1985
			JP 1663348 C	19-05-1992
			JP 3026455 B	10-04-1991
			JP 60055517 A	30-03-1985

